

RECLAIMED WOOD OAK

AHEI: Reclaimed wood oak with a surface full of character, contrasting colour variations are a valued feature, sound knots, black knots, spike knots acceptable, heartwood, partial rot, irregular wormholes, shakes, nail holes, material inclusions, bark pockets as well as mechanical damages acceptable. Lamellas are joint free placed but not joint free glued.

Bottom layer: Oak, no special quality specifications, holes are not filled.



The above picture shows an example of the natural character of the wood, this will vary in every panel.

Characteristics

Grading	Thickness mm app.	Length mm (Width 2030 mm)	Top layer thickness mm	Top layer width mm	Middle layer	Packaging pack./palett
AHEI/C	19	2000-2500 (subject to availability)	3,8	Mix	SML Softwood	30

Panels are glued SWP/2 NS (non structural): solid wood panels for non-structural use in wet areas, with regard to appropriate constructional protection also suitable for exterior use (sheltered areas).

Legend: SML = strip core, BML = board middle layer.

More information concerning fire classification in the accompanying information to CE-marking.

Technical information

More information (for example concerning fire classification) in the accompanying information to CE-marking at <http://www.admonter.eu/en/downloads>

Type of wood	Thickness (mm)	Middle layer	Weight [kg/m ²]	Moisture content [%]	Lambda [W/m K]
Reclaimed Wood Oak	19	Spruce	10,4	7+/-2	0,14



You can find more detailed information at: admonter.at

The above picture shows an example of the natural character of the wood, this will vary in every panel. Variations in colour and grain patterns are natural and inevitable. A picture is never a substitute for the "real thing". For this reason we recommend a visit to your nearest Admonter dealer. He will be pleased to show you samples.

ELEMENTS