Reclaimed wood sunbaked brushed



AHS: Reclaimed wood panel with a surface full of character and colour variation; heartwood, resin pockets, nail holes, treenails, spike knots, knots, black knots, bark pockets and worm holes acceptable; shakes, mechanical damages and blue stain conditionally acceptable, surface defects professionally filled (some are open); Colour range: mostly brown with typical for reclaimed wood partially colour (grey/brown/black); Surface: the textured surface is caused by natural weathering of the wood; strong brushed; top layers joint free placed. Bottom layer C: Spruce; no special quality specification, not filled. This panel is also available with a gluing adapted to wet areas (sauna) and is therefore in accordance with the emission requirements according to ÖNORM M6219-1:2010 for the use in sauna areas (see information "Admonter Element's in sauna areas" at http://www.admonter.eu/en/downloads/).









Grading	Thickness mm app.	Length in mm (Width 2030 mm)	Top layer Thickness mm	Top layer Width mm	Middle layer	Packaging pack./palett
AHS/C (suitable for sauna use)	22	1800 - 3900 (subject to availability)	7 - 10	Mix	BML or SML-Spruce (subject to availability)	25

Panels are glued SWP/2 NS (non structural): solid wood panels for non-structural use in wet areas, with regard to appropriate constructional protection also suitable for exterior use (sheltered areas). **Legend:** SML = strip core, BML = board middle layer.

Technical information									
More information (for example concerning fire classification) in the accompanying information to CE-marking at									
Type of wood	Thickness (mm)	Middle layer	Weight [kg/m²]	Moisture content [%]	Lambda [W/m K]				
Reclaimed Wood sunbaked	22	Spruce	10,3	7+/-2	0,12				



























Reclaimed wood sunbaked brushed



Wooden panels Elements

Characteristics:







































