

SPRUCE AGED

AB: Virtually only sound knots, small knot holes are professionally filled, occasional pith ray and resin pockets possible, no shakes, the ageing process affects the entire depth of the top layer and this colour similar to reclaimed wood will not fade away like a surface stain, slight compression wood and colour variation possible, joint free gluing

Bottom layer standard: Spruce aged: closed jointing, no blue-stain.



The above picture shows an example of the natural character of the wood, this will vary in every panel.

Characteristics

Grading	Thickness mm app.	Length mm (Width 2030 mm)	Top layer thickness mm	Top layer width mm	Middle layer	Packaging pack./palett
AB/ST	19	5000	5	137/142	BML Spruce	30

Panels are glued SWP/2 NS (non structural): solid wood panels for non-structural use in wet areas, with regard to appropriate constructional protection also suitable for exterior use (sheltered areas).

Legend: SML = strip core, BML = board middle layer.

More information concerning fire classification in the accompanying information to CE-marking.

Technical information

More information (for example concerning fire classification) in the accompanying information to CE-marking at <http://www.admonter.eu/en/downloads>

Type of wood	Thickness (mm)	Middle layer	Weight [kg/m ²]	Moisture content [%]	Lambda [W/m K]
Spruce aged	19	Spruce	8,8	8+/-2	0,12



You can find more detailed information at: admonter.at

The above picture shows an example of the natural character of the wood, this will vary in every panel. Variations in colour and grain patterns are natural and inevitable. A picture is never a substitute for the "real thing". For this reason we recommend a visit to your nearest Admonter dealer. He will be pleased to show you samples.

ELEMENTS