

# LARCH AGED

**AB:** black knots, knotholes are filled with natural knot plugs, small filled knots, occasional pith ray, occasional resin pockets, no sapwood, slight compression wood and slight colour variations possible, jointfree gluing, the ageing process affects the entire depth of wear layer, warm brown colour similar to reclaimed wood.

**Bottom layer standard:** Larch aged: closed jointing, professionally filled with natural knot plugs, no blue-stain.

ELEMENTS



The above picture shows an example of the natural character of the wood, this will vary in every panel.

Characteristics

Grading	Thickness mm app.	Length mm (Width 2030 mm)	Top layer thickness mm	Top layer width mm	Middle layer	Packaging pack./palett
AB/ST	19	3900	3,6	186	SML Larch	30
AB/AB	40	2000/2400	3,6	158	Spruce 5-Layer	10

**Panels are glued SWP/2 NS (non structural):** solid wood panels for non-structural use in wet areas, with regard to appropriate constructional protection also suitable for exterior use (sheltered areas).

**Legend:** SML = strip core, BML = board middle layer.

More information concerning fire classification in the accompanying information to CE-marking.

### Technical information

More information (for example concerning fire classification) in the accompanying information to CE-marking at <http://www.admonter.eu/en/downloads>

Type of wood	Thickness (mm)	Middle layer	Weight [kg/m <sup>2</sup> ]	Moisture content [%]	Lambda [W/m K]
Larch aged	19	Larch aged	10,8	8+/-2	0,14
	40	Spruce	19,6	8+/-2	0,13



You can find more detailed information at: [admonter.at](http://admonter.at)

The above picture shows an example of the natural character of the wood, this will vary in every panel. Variations in colour and grain patterns are natural and inevitable. A picture is never a substitute for the "real thing". For this reason we recommend a visit to your nearest Admonter dealer. He will be pleased to show you samples.